



**GAUS Group d.o.o. Požarevac**  
**Strahinjica Bana B2-3**  
**12 000 Požarevac, Srbija**  
**e-mail: office@gausgroup.com**

**Phone: ++381 (0)12 530 700**  
**++381 (0)60 386 0000**  
**Fax: ++381 (0)12 530700**  
**www.gausgroup.com**

**KARAKTERISTIKE  
 NEO MAGNETA**

Material	Remanence Br				Coercivity HcB				Intrinsic Coercivity HcJ		Max Energy Product				Max. Working Temp.
	kGs		T		kOe		kA/m		kOe	kA/m	MGOe		kJ/m <sup>3</sup>		°C(L/D=0.7)
	Typ.	Min	Typ.	Min	Typ.	Min	Typ.	Min	Min	Min	Typ.	Min	Typ.	Min	Max
NEO 35	12.2	11.7	1.22	1.17	11.2	10.5	891	836	12	955	35	33	279	263	80
NEO 38	12.6	12.2	1.26	1.22	11.2	10.5	891	836	12	955	38	35	302	279	80
NEO 40	13.0	12.6	1.30	1.26	11.2	10.5	891	836	12	955	40	38	318	302	80
NEO 42	13.3	13.0	1.33	1.30	11.2	10.5	891	836	12	955	42	40	334	318	80
NEO 45	13.7	13.3	1.37	1.33	11.2	10.5	891	836	12	955	45	42	358	334	80
NEO 48	14.1	13.7	1.41	1.37	10.8	10.5	859	812	11	875	48	45	382	358	80
MEO 50	14.4	14.0	1.44	1.40	10.8	10.2	859	811	11	875	50	48	399	383	70
NEO 33 M	11.7	11.4	1.17	1.14	10.8	10.2	859	812	14	1114	33	30	263	239	100
NEO 35 M	12.2	11.7	1.22	1.17	11.2	10.5	891	836	14	1114	35	33	279	263	100
NEO 38 M	12.6	12.2	1.26	1.22	11.5	10.8	915	859	14	1114	38	35	302	279	100
NEO 40 M	13.0	12.6	1.30	1.26	11.5	10.8	915	859	14	1114	40	38	318	302	100
NEO 42 M	13.3	13.0	1.33	1.30	11.5	10.8	915	859	14	1114	42	40	334	318	100
NEO 45 M	13.7	13.3	1.37	1.33	11.5	10.8	915	859	14	1114	45	42	358	334	100
NEO 48 M	14.1	13.7	1.41	1.37	11.5	10.8	915	859	14	1114	48	45	383	359	90
NEO 30 H	11.4	10.8	1.14	1.08	10.2	9.8	812	780	17	1353	30	28	239	223	120
NEO 33 H	11.7	11.4	1.17	1.14	11.2	10.2	875	812	17	1353	33	30	263	239	120
NEO 35 H	12.2	11.7	1.22	1.17	11.2	10.5	891	836	17	1353	35	33	279	263	120
NEO 38 H	12.6	12.2	1.26	1.22	11.5	10.8	915	859	17	1353	38	35	302	279	120
NEO 40 H	13.0	12.6	1.30	1.26	11.5	10.8	915	859	17	1353	40	38	318	302	120
NEO 42 H	13.3	13.0	1.33	1.30	11.5	10.8	915	859	17	1353	42	40	334	318	120
NEO 44 H	13.6	13.3	1.36	1.33	11.5	10.8	915	859	17	1353	44	42	350	334	120
NEO 46 H	13.8	13.5	1.38	1.35	11.5	10.8	915	859	17	1352	46	44	367	351	120
NEO 48 H	14.1	13.7	1.41	1.37	11.5	10.8	915	859	17	1352	48	45	383	359	120
NEO 27 SH	10.6	10.2	1.06	1.02	10.5	9.6	836	764	20	1592	25	27	199	215	150
NEO 30 SH	11.4	10.8	1.14	1.08	10.2	9.8	812	780	20	1592	30	28	239	223	150
NEO 33 SH	11.7	11.4	1.17	1.14	11.0	10.2	875	812	20	1592	33	30	263	239	150
NEO 35 SH	12.2	11.7	1.22	1.17	11.2	10.5	891	836	20	1592	35	33	279	263	150
NEO 38 SH	12.6	12.2	1.26	1.22	11.5	10.8	915	859	20	1592	38	35	302	279	150
NEO 40 SH	13.0	12.6	1.30	1.26	11.5	10.8	915	859	20	1592	40	38	318	302	150
NEO 42 SH	13.3	13.0	1.33	1.30	11.5	10.8	915	859	20	1591	42	40	335	319	150
NEO 44 SH	13.6	13.3	1.36	1.33	11.5	10.8	915	589	20	1591	44	42	351	335	150
NEO 28 UH	10.8	10.4	1.08	1.04	10.2	9.8	812	780	25	1989	28	25	223	199	160
NEO 30 UH	11.4	10.8	1.14	1.08	10.6	10.0	844	796	25	1989	30	28	239	223	160
NEO 33 UH	11.7	11.4	1.17	1.14	11.0	10.2	875	812	25	1989	33	30	263	239	160
NEO 35 UH	12.2	11.7	1.22	1.17	11.2	10.5	891	836	25	1989	35	33	279	263	160
NEO 38 UH	12.6	12.2	1.26	1.22	11.5	10.5	915	835	25	1989	38	35	303	279	160
NEO 40 UH	13.0	12.6	1.30	1.26	11.5	10.5	915	835	25	1989	40	38	319	303	160
NEO 28 EH	10.8	10.4	1.08	1.04	10.2	9.8	812	780	30	2387	28	25	223	199	180
NEO 30 EH	11.4	10.8	1.14	1.08	10.6	10.0	844	796	30	2387	30	28	239	223	180
NEO 33 EH	11.7	11.4	1.17	1.14	11.0	10.2	875	812	30	2387	33	30	263	239	180
NEO 35 EH	12.2	11.7	1.22	1.17	11.5	10.5	915	835	30	2387	35	33	279	263	180
NEO 38 EH	12.6	12.2	1.26	1.22	11.5	10.5	915	835	30	2387	38	35	303	279	180

Standardne klase koje isporučujemo : N38, N42, N35. Na zahtev klijenta moguća isporuka i drugih klasa.